

SPECIFICATION

PVC CLEAR **1.0mm**

Tensile Strength (kg/cm ²)	MD	> 278
<i>ASTM D-882 method A</i>	CD	> 230

Elongation (%)	MD	> 350
<i>ASTM D-882 method A</i>	CD	> 387

Tear Strength (kg/mm)	MD	> 8.2
<i>ASTM D-1004</i>	CD	> 8.7

Dimensional Stability (%)	MD	> -4.0
(23°C/24hrs)	CD	< 1.0
<i>ASTM D-1004</i>		

Shrinkage (100°C/30 min)	MD	< 3.0
<i>ASTMD D-1204</i>	CD	< 2.0

Weight gr/m ²	1400
--------------------------	------

Width in cms	140
--------------	-----

Peel Strenght Kg/3cm: > 4
T-210

Coldcrack: -20° C

MD = machine direction

CD = cross direction

ASTMD = American Standard Test Methode